



Crawl Space Vapor Barrier

20 Mil

PROPERTIES	TEST METHOD	SPECS
Appearance		White/White
Thickness, Nominal		20 mil max
Weight		14 oz./yd ²
Construction		Extrusion laminated with scrim reinforcement
1" Tensile Strength	ASTM D7003	90 lbf/in
Tensile Elongation at Scrim Break	ASTM D7003	16%
Tensile Elongation at Film Break	ASTM D7003	760%
Grab Tensile	ASTM D7004	140 lbf
CBR Puncture Resistance	ASTM D6241	340 lbf
*Tongue Tear	ASTM D5884	63 lbf
**Trapezoid Tear	ASTM D4533	85 lbf
Mullen Burst	ASTM D751	170 psi
Maximum Use Temp.		180°F
Minimum Use Temp.		-70°F
WVTR	ASTM E96 Procedure B	0.130 grains/(100in ² -day)
Perm Rating	ASTM E96 Procedure B	0.019 grains/(ft ² -hr-in Hg)

WhiteCap Liner is a multi ply polyethylene laminate. The liner is reinforced with polyester cord reinforcement. WhiteCap liner is flame retardant.

* Tests are an average of MD & TD directions. ** Tests are an average of diagonal directions.