



PROPERTIES	TEST METHOD	SPECS
Appearance		White/Blue
Thickness, Normal		20 mil max/ 16 mil min.
Weight per OZ./YD ²	ASTM D-3776	9.93 oz./yd ²
Construction		Multi ply polyethylene w/ polyester cord reinforcement
Tensile Grab	ASTM D-751	Warp Fill 93.4 / 72.3
Elongation % Peak 1"	ASTM D-751	Warp Fill 456.6 / 499.6
Trapezoid Tear LBS:	ASTM D-4533	Warp Fill 61.7 / 47.4
Maximum Use Temp.		180 F
Vapor Transmission Procedure B temp: 73.4 F Humidity: 50% RH	ASTM E-96	1.7 gms./sq.meter/24 hrs.
Flame Spread Index	ASTM E-84-95	0
Smoke Developed Value	ASTM E-84-95	45

WhiteCap Liner a white/green multi ply polyethylene laminate. The liner is reinforced with polyester cord reinforcement. WhiteCap liner is flame retardant.

* These are typical properties and are intended as a general guide only, not as specification limits.